

Advanced Materials**RenLam[®] LY 5210
Ren[®] HY 5211 Slow or HY 5212 Fast**

LAMINATING RESIN
EPOXY HIGH TEMPERATURE, SPEED CONTROLLED, LAMINATING SYSTEM

KEY PROPERTIES

- Exceptionally high temperature resistance.
- Variable speed of cure control.
- Excellent fiber wet-out properties due to low viscosities.
- Partial cure at room temperature completed with indicated post cure.
- Excellent inter layer adhesion.

APPLICATIONS

- Extremely large tools can be produced due to very long pot life.
- Tools requiring heat resistance up to 200° C.
- Fast and medium hardeners allow better control over reaction.
- For heat resistant tools used with glass or carbon fibers.
- Pre-preg lay-up tools.

PRODUCT DATA

Property	Unit	RenLam [®] LY 5210	Ren [®] HY 5211	Ren [®] HY 5212
Appearance Colour	visual	Liquid Pale beige	Liquid Clear, pale yellow	Liquid Clear, pale yellow
Viscosity at 25°C	mPa s	3000	650	350
Density	g/cm ³	1.2	1.01	1.01

PROCESSING

Mix ratio	Parts by weight	
RenLam [®] LY 5210	100	100
Ren [®] HY 5211	40	
Ren [®] HY 5212		40

Mix the two components thoroughly in the ratio indicated, then impregnate each layer of cloth as it is laid up to construct the laminate.
Post-curing is essential to benefit the final properties.



PROPERTIES


Resin/Hardener mix:	Volume	Unit	LY 5210 HY 5211 Slow	LY 5210 HY 5212 Fast
Appearance			Amber	Amber
Viscosity at 25°C		mPa s	2400	2000
Pot life at 25°C	500 ml	hours	24	12
Gel time thin layer			2 days	18 hours
Time to tack thin layer			3 days	20 hours
Length of tack time			2 days	18 hours

AFTER CURE

24 hours RT+ 12hours @40 °C + 2hours @80 °C + 2hours @100 °C + 2hours @120 °C + 2hours @140 °C + 2hours @160 °C+ 2hours @180 °C + 12hours @ 200 °C and slowly cooled down to RT

Density	ISO 1183	g/cm ³	1.1	1.1
Hardness	ISO 868	Shore	85 D	85 D
Flexural strength	ISO 178	MPa	110	88
Flexural modulus	ISO 178	MPa	3300	3500
Compressive strength	ISO 604	MPa	130	153
Deflection temperature	ISO 75	°C	190	223
T.g.	DSC	°C	200	238
Impact strength	Charpy	KJ / m ²	2.5	3



**STORAGE**

The resin described in this instruction sheet has the shelf life shown provided it is stored at +2 - 8°C in a dry place and in sealed containers, preferably those in which they are supplied.

The hardeners described in this instruction sheet have the shelf lives shown provided they are stored at +6 - 28°C in a dry place and in sealed containers, preferably those in which they are supplied.

WORKING CONDITIONS

The product should be used when in the temperature range 18-25°C.

PACKAGING

System	LY 5210	HY 5211	HY 5212
Quantity and Weight	25 kg	20 kg	20 kg
Quantity and Weight	4x5 kg		4x5 kg
Quantity and Weight			165 kg

HANDLING PRECAUTIONS**Caution**

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Ren and RenLam are registered trademarks of Huntsman Corporation or an affiliate thereof.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Office :
Huntsman Advanced Materials (Switzerland) GmbH
Klybeckstrasse 200
CH-4057 BASEL
Switzerland
+41 61 299 1111