

Composite Resin Systems

Wet Lay-Up Process

Product Designation	Pot Life	Mix Viscosity	Glass Transition Temperature*	Flexural Strength*	Ultimate Flexural Elongation*	Key Features
Conditions	RT/100 ml	77°F	DSC, 10K/min	77°F	77°F	
Norm			IEC1006	ISO 178	ISO 178	
Unit	min	cps	°F	Kpsi	%	
Araldite® LY 3505 / XB 3403	600 - 720	300 - 400	173 - 181	16.0 - 18.8	10.5 - 13.0	Reactivity can be adjusted on demand
Araldite® LY 3505 / Aradur® 3405	26 - 36	1000 - 1200	189 - 197	19.6 - 22.5	7.0 - 9.0	
Araldite® LY 1556 / Aradur® 3405	40 - 50	1500 - 1800	197 - 208	18.8 - 21.0	9.0 - 11.0	Higher viscosity for vertical application

* Cure schedule 4 hrs @ 140°F + 6 hrs @ 176°F
Further systems are available upon request.

Infusion Process

Product Designation	Pot Life	Mix Viscosity	Glass Transition Temperature	Flexural Strength	Ultimate Flexural Elongation	Key Features
Conditions	RT/100 ml	77°F	DSC, 10K/min	77°F	77°F	
Norm			IEC1006	ISO 178	ISO 178	
Unit	min	cps	°F	Kpsi	%	
Araldite® LY 1564 / Aradur® 3486	560 - 620	200 - 300	176 - 183	17.1 - 18.8	10.5 - 12.5	
Araldite® LY 1564 / Aradur® 3416	290 - 340	200 - 320	176 - 185	17.1 - 18.8	10.0 - 12.0	
Araldite® LY 1564 / Aradur® 3487	130 - 160	220 - 320	178 - 187	17.1 - 18.8	10.0 - 12.0	
Araldite® LY 1568 / Aradur® 3489	850 - 950	200 - 300	170 - 176	17.4 - 18.8	9.0 - 10.0	
Araldite® LY 1568 / Aradur® 3491	750 - 850	200 - 300	165 - 176	17.4 - 18.8	9.0 - 10.0	New! Low exotherm
Araldite® LY 1568 / Aradur® 3492	300 - 350	250 - 350	176 - 185	18.1 - 19.6	7.0 - 7.5	

* Cure schedule 8 hrs @ 176°F

Filament Winding Process

Product Designation	Pot Life	Mix Viscosity	Glass Transition Temperature	Flexural Strength	Ultimate Flexural Elongation	Key Features
Conditions	RT / 100 ml	77°C	DSC, 10K/min	77°C	77°C	
Norm			IEC1006	ISO 178	ISO 178	
Unit	hrs	cps	°F	Kpsi	%	
Araldite® LY 556 / Aradur® 917 / Accelerator DY 070	95 - 115	600 - 900	289 - 302	18.8 - 21.8	7.0 - 8.5	High Tg for winded parts

* Cure schedule 4 hrs @ 176°F + 8 hrs @ 284°F

Prepreg Process

Product Designation	B-Staging	Shelf Life	Glass Transition Temperature	Flexural Strength	Ultimate Flexural Elongation	Description
Conditions		@ 73.4 °F	DSC, 10K/min	77°F	25°C	
Norm			IEC1006	ISO 178	ISO 178	
Unit			°F	Kpsi	%	
Araldite® LY 1556 / Aradur® 1571 / Accelerator 1573 / XB 3403	24 hrs at 23°C	> 6 weeks	221 - 239	18.1 - 20.3	7.0 - 10.0	Easy B-staging
XU 3508 / Aradur® 1571 / Accelerator 1573 / XB 3403	24 hrs at 23°C	> 1 month	240 - 257	16.0 - 17.4	5.5 - 8.0	Toughened prepreg with easy B-staging

* Cure schedule 2-4 hrs @ 284°F
All systems are Germanische Lloyd (GL) approved

Global Presence – 13 Manufacturing Sites



HUNTSMAN

Enriching lives through innovation

HUNTSMAN

Enriching lives through innovation

Advanced Materials

Renewable Energy Efficiency

Tooling, Composites, Adhesives and Repair Solutions
Wind Selector Guide



For More Information

www.huntsman.com/advanced_materials
advanced_materials@huntsman.com

Americas:

Huntsman Advanced Materials Americas
10003 Woodloch Forest Drive
The Woodlands
Texas 77380
USA
Tel. +1 888 564 9318
Fax +1 281 719 4047

Europe/Africa:

Huntsman Advanced Materials (Switzerland) GmbH
Klybeckstrasse 200
P.O. Box
4002 Basel
Switzerland
Tel. +41 61 299 11 11
Fax +41 61 299 11 12

India/MiddleEast:

Huntsman Advanced Materials (India) Pvt. Ltd.
5th Floor, Bldg. No. 10
Solitaire Corporate Park, 167
Guru Hargovindji Marg, Chakal, Andheri (East)
Mumbai – 400 093
India
Tel. +91 22 4095 1556-60
Fax + 91 22 4095 1300/1400/1500

Asia/Pacific:

Huntsman Advanced Materials (Guangdong) Co., Ltd.
Rooms 4604 – 4608, Maxdo Center
8 Xing Yi Road
Shanghai, 200336
P.R. China
Tel. +86 21 2208 7588
Fax +86 21 2208 7511

Legal Information

Araldite, Aradur, Arathane, Ren, RenLam, RenGel and RenPaste are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries. Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. or Huntsman Advanced Materials (Guangdong) Co., Ltd. ("Huntsman"). The following supercedes Buyer's documents. While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Data and results are based on controlled conditions and/or lab work. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights. The Product may be or become hazardous. Buyer should (i) obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, (ii) take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product and (iii) comply with and ensure that its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product comply with all safety information contained in the applicable Material Safety DataSheets, Technical Data Sheets or other instructions provided by Huntsman and all applicable laws, regulations and standards relating to the handling, use, storage, distribution and disposal of and exposure to the Product. Please note that products may differ from country to country. If you have any queries, kindly contact your local Huntsman representative.

© 2010 Huntsman Corporation. All rights reserved.

Wind Market

As a global partner and innovator working in collaboration with all major wind energy equipment manufacturers, Huntsman Advanced Materials has all the right technologies and high-performance products the industry requires. Our products are used in applications ranging from plugs and patterns, to complete composite turbine production as well as assembly and repair. Our range includes standard products as well as custom-made solutions formulated to answer specific project requirements.

Huntsman Advanced Materials

Huntsman Advanced Materials is a leading global supplier of synthetic and formulated polymer systems for customers requiring high-performance materials which outperform the properties, functionality and durability of traditional materials. Over 2,300 associates at 13 locations worldwide work to fulfill this promise every day.

We enjoy a long heritage of pioneering technological excellence and offer a unique and wide range of innovative and tailor-made solutions to more than 9,000 customers in over 90 different countries. We maintain leading positions in our key markets through product differentiation, technical support and customer focus. The primary markets we serve include coatings, construction, electronics, adhesives and inks, medical, marine, power transmission and distribution, general industry, aerospace, wind power generation, automotive and sports equipment.

Blade Assembly

Product	Description	Mix Ratio (pbv)	Pot Life (500gr, 73.4°F) (min.)	Recommended Cure Schedule	LSS psi (MPa)*	Typical Cured Tg °F (°C)**	Key Features
Araldite® AW 4856 / Hardener HW 4856	EP system GL approved	100:50	240 - 280 (70°C)	5 hrs, 158°F	3190-3625 (22- 25)	163.4-174.2 (73 - 79)	Low exotherm, low shrinkage, high fracture toughness resistance
Araldite® AW 4856 / Hardener HW 4856 fast	EP system	100:50	40 - 60 (70°C)	5 hrs, 158°F	3190-3625 (22- 25)	163.4-174.2 (73 - 79)	Fast handling
Arathane® 3427 PO / Arathane® 3304 IS	PU system	100:45	100 - 120*** (60°C)	2 hrs, 140°F	1450-1740 (10 - 12)	104-122 (40-50)	

* on epoxy composite

** cured in standard blade cycle after initial fixing of shear webs at 25°C, IEC 1006, DSC, 10K/min

*** for 100 gr

Fast Assembly and Repair

Product	Description	Repair			Mix Ratio (pbv)	Pot Life (100gr, 23°C) (min.)	Recommended Cure Schedule	LSS psi (MPa)*	Typical Cured Tg °F (°C)**	Gap Filling in. (mm)	Key Features
		Plugs	Composite Molds	Blades							
Araldite® 2021	MMA system	•	•	•	1:1	3 - 7	1hr, ambient cure	2900 - 3190 (20 - 22)	149 - 176 (65 - 80)	.12" - 0.2" (3 - 5)	Fast-setting, tough adhesive for rapid fixing and filling of small voids
Araldite® 2022	MMA system	•	•	•	1:1	8 - 15	2hrs, ambient cure	2900 - 3190 (20 - 22)	149 - 176 (65 - 80)	.12" - 0.2" (3 - 5)	Medium open time and fast-curing tough adhesive for field/workshop operations
Arathane® 4497 PO / Arathane® 3304 IS	PU system	•	•	•	100:52	8 - 15	2 hrs, 60°C	2175 - 2610 (15 - 18)	104 - 122 (40 - 50)	.12" - 0.2" (3 - 5)	Fast-setting, ideal for filling holes
Araldite® LY 1564 / XB 3458	EP system			•	100:20	13 - 17	7 days, 23°C 15 min, 80°C	n/a	136 - 151 (58 - 66) 190 - 205 (88 - 96)	n/a	Wet lay-up repair process, good toughness resistance
Araldite® LY 3297 / Aradur® 3298	EP system			•	100:40	120 - 135	7 days, 23°C 1 day, 23°C + 4hrs, 90°C	n/a	129 - 138 (54 - 59) 198 - 208 (92 - 98)	n/a	Wet lay-up repair process, longer handling time
Araldite® LY 3297 / Aradur® 3299	EP system			•	100:40	40 - 50	7 days, 23°C 1 day, 23°C + 4hrs, 90°C	n/a	129 - 138 (54 - 59) 210 - 221 (99 - 105)	n/a	

* on aluminium

** cured in standard blade cycle after initial fixing of shear webs at 77°F, IEC 1006, DSC, 10K/min



Auxiliary Bonding

Product	Description	Mix Ratio (pbv)	Pot Life (100gr, 73.4°F) (min.)	Recommended Cure Schedule	LSS psi (MPa)*	Typical Cured Tg °F (°C)**	Gap Filling in. (mm)	Key Features
Araldite® 2014	EP system	2:1	50 - 65	Ambiant or 4hrs at 140°F	2175 - 2610 (15 - 18)	145.2 - 185 (79 - 85)	0.2 (5)	Bonding tip, control shaft components, high temperature and chemical resistance, ideal for metals
Araldite® 2015	EP system GL approved	1:1	45 - 60	Ambiant or 4hrs at 140°F	2175 - 2610 (15 - 18)	122.6 - 176 (67 - 80)	0.4 (10)	Bonding of lightning conductor, monitor sensors, ideal for dissimilar substrates
Araldite® 8579 Resin / Hardener 8579	EP system	100:40	40 - 55	Ambiant or 4hrs at 140°F	2175 - 2610 (15 - 18)	174.2 - 185 (79 - 85)	0.2 (5)	Tip control shaft and vibration damper bonding
Araldite® AV 4076-1 / Hardener HV 5309-1	EP system GL approved	1:1	50 - 65	Ambiant or 4hrs at 140°F	2900 - 3480 (20 - 24)	122.6 - 176 (67 - 80)	0.2 - 0.4 (5 - 10)	Steel insert bonding
Araldite® AW 4510 / Hardener HW 4511	EP system	2:1	85 - 100	2hrs at 140°F	2030 - 2320 (14 - 16)	230 - 257 (110 - 125)	0.4 (10)	High-temperature application

* on epoxy composite

** cured in standard blade cycle after initial fixing of shear webs at 25°C, IEC 1006, DSC, 10K/min

Tooling Systems

Master Model / Plug

Seamless Modeling Pastes:

Product designation	Color	Minimum Cure Schedule	Density lb/ft³ (g/cm³)	Shore Hardness D (ISO 868)	Coefficient of Thermal Expansion in./in.-°F (m/m-°C)	Tg, by DMA °F (°C)	Compressive Strength psi (MPa)	Flexural Strength psi (MPa)
RenPaste® SV 4503-1 / Ren® HV 4503-1	Brown	Machinable after 1 day (RT* curing)	47.3 (0.76)	60	54 x 10 ⁻⁶ (3 days @ RT*) (101 x 10 ⁻⁶)	159 (70.6)	2100 (14.5)	2200 (15.2)
RenPaste® 4618/ Ren® HV 4619	Grey	Machinable after 1 day (RT* curing)	56 (0.90)	76	30 x 10 ⁻⁶ (7 days @ RT*) (54 x 10 ⁻⁶)	230 (110)	9280 (67.7)	5220 (36)

*Room Temperature 77°F

Remark: Machine Applied

Mold Production with Infusion and Wet Lay-Up Processes (Heat resistant up to 248°F 120°C)

Surface Coat:

Product Designation	Color	Gel Time Thin Layer (77°F/min)	Shore Hardness D (ISO 868)	Flexural Strength psi (MPa)	Coefficient of Thermal Expansion in./in.-°F (m/m-°C)	Tg, by DMA °F (°C)
RenGel® 4026R / Ren® 1500H	Dark Grey	50 - 60	90	8500 (58.6)	37 x 10 ⁻⁶ (66.6 x 10 ⁻⁶)	310 (154.4)
RenGel® 4026R / Ren® 1501H	Dark Grey	30 - 40	90	8000 (55.2)	32 x 10 ⁻⁶ (57.6 x 10 ⁻⁶)	310 (154.4)
RenGel® 4026R / Ren® 1510H	Dark Grey	2 hrs	90	8700 (60)	38 x 10 ⁻⁶ (68.4 x 10 ⁻⁶)	335 (168.3)

Back Construction:

Product Designation	Color	Viscosity at 77°F (cP)	Gel Time (77°F/min)	Coefficient of Thermal Expansion in./in./°F (m/m-°C)	Tg °F (°C)	Flexural Strength psi (MPa)	Process
RenLam® 4005R/ Ren® 1500H	Clear to pale yellow	1900	50	8.5 x 10 ⁻⁶ (15.1 x 10 ⁻⁶)*	338 (170) by DMA	35000 (241.4)*	Wet lay-up / Infusion
RenLam® 4005R / Ren® 1510H	Clear to pale yellow	3300	160	8.5 x 10 ⁻⁶ (15.1 x 10 ⁻⁶)*	329 (165) by DMA	29000 (200)*	Wet lay-up / Infusion
Araldite® LY 1564 / Aradur® 22962	Clear liquid	400 - 600	110 - 150		230 (110) @ 4hrs / 176°F 302 (150) fully cured by DSC	17980 (124)**	Infusion
Araldite® LY 1564 / Aradur® 2954	Clear liquid	500 - 700	480 - 600	40 x 10 ⁻⁶ (72 x 10 ⁻⁶)**	212 (100) 4hrs / 176°F 311 (155) fully cured by DSC	17400 (120)**	Infusion

* 10 oz. Glass Cloth Laminate

** Neat Casting

Mold Production with Infusion and Wet Lay-Up Process (Heat resistance up to 356°F 180°C)

Surface Coat:

Product Designation	Color	Pot Life at 77°F (hr)	Shore Hardness D (ISO 868)	Demolding Time (hr)	Cure Cycle (time/°F)	Tg by DSC °F (°C)
RenGel® SW 5200 / Ren® HY 5212	Black	10 (500 ml)	90	14 hrs @ 40 - 50°C	12 hrs / 104 + 2 hrs / 176 + 2 hrs / 212 + 2 hrs / 248 + 2 hrs / 284 + 2 hrs / 320 + 2 hrs / 356 + 12 hrs / 392	392 (200)

*Room Temperature

Back Construction:

Product Designation	Color	Viscosity at 77°F (cP)	Pot Life at 77°F (500 ml) (hr)	Demolding Time (hr)	Cure Cycle (time/°F)	Tg °F (°C)	Flexural Strength (ISO 178) psi (MPa)	Process
RenLam® LY 5210 / Ren® HY 5212	Amber	2000	12	14 hrs @ 104 - 122°F	12hrs / 104 + 2 hrs / 176 + 2 hrs / 212 + 2 hrs / 248 + 2 hrs / 284 + 2 hrs / 320 + 2 hrs / 356 + 12 hrs / 392	446 - 460 (230 - 238) by DSC	12760 (88)	Wet lay-up
Araldite® LY 8615 / Aradur® 8615	Amber	550	18 (100 ml)	24 hrs @ 104°F	24 hrs / 104 + 2 hrs / 140 + 2 hrs / 176 + 2 hrs / 212 + 2 hrs / 248 + 2 hrs / 284 + 2 hrs / 320 + 3 hrs / 356	428 (220) by DMA	14500 (100)	Infusion

*Room Temperature